



AMERICAN FLAMECOAT INC.

520 Eagleton Downs Drive - D
 Pineville, NC 28134
 O: 704.405.2550
 F: 704.543.9772
 www.americanflamecoat.com

thesign / E. STIEGER Company
 NEUSEELAND 32
 9404 RORSCHACHERBERG
 SWITZERLAND

Pattern: PARK color: 890 – Treated with Flamecoat and Fibercare
 Report No.: 75027
 Date: March 10, 2017

TEST RESULTS

NATIONAL FIRE PROTECTION ASSOCIATION STD.701-2015 – TEST 1 Small Scale

Specimen	Residues (seconds)	Weight loss (%)
1	0	14
2	0	15
3	0	18
4	0	17
5	0	14
6	0	16
7	0	11
8	0	9
9	0	14
10	0	15
Average	0	14.3

Results: The Above Tested Material *Meets* the Requirement

Requirements:

Average percent weight loss can-not exceed 40% and any individual Specimen can-not exceed mean value plus three standard deviations.

Residue Flame:

Shall not continue to flame after reaching the floor of the tester for more than an average of two seconds per specimen for the sample of 10 specimens.

Sincerely,

Brad Souffrant

