



## AMERICAN FLAMECOAT INC.

520 Eagleton Downs Drive - D  
Pineville, NC 28134  
O: 704.405.2550  
F: 704.543.9772  
[www.americanflamecoat.com](http://www.americanflamecoat.com)

thesign / E. STIEGER Company  
NEUSEELAND 32  
9404 RORSCHACHERBERG  
SWITZERLAND

Pattern: RICHMOND color: 800 – Treated with Flamecoat and Fibercare  
Report No.: 75027  
Date: March 10, 2017

### TEST RESULTS

#### NATIONAL FIRE PROTECTION ASSOCIATION STD.701-2015 – TEST 1 Small Scale

Specimen	Residues (seconds)	Weight loss (%)
1	0	19
2	0	22
3	0	16
4	1	20
5	0	21
6	0	23
7	0	18
8	0	16
9	1	19
10	0	20
Average	0.2	19.4

**Results:** The Above Tested Material **\*Meets\*** the Requirement

**Requirements:**

Average percent weight loss can-not exceed 40% and any individual Specimen can-not exceed mean value plus three standard deviations.

**Residue Flame:**

Shall not continue to flame after reaching the floor of the tester for more than an average of two seconds per specimen for the sample of 10 specimens.

Sincerely,

Brad Souffrant

