



Confidential Report

Our Ref: 23/61308D1/08/23





Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: onestopshop@bttg.co.uk
Website: www.bttg.co.uk

Date: 30 August 2023

Our Ref: 23/61308D1/08/23

Your Ref: ---

Page: 1 of 4

Client:

The Sign AG

Neuseeland 32
9404 Rorschacherberg
Switzerland

Job Title:

Fire Test on One Fabric Sample

Clients Order Ref:

--

Date of Receipt:

16 August 2023

Date Test Started:

24 August 2023

Description of Sample:

One sample of fabric, which was referenced by the client as;
30483 Polo Club

Work Requested:

We were asked to make the following fire test:
BS 5852: Clause 11:2006 (2011)

- * subcontracted test, UKAS accredited
- ** subcontracted test, EN ISO/IEC 17025 accredited
- *** not UKAS accredited



1066

Note: This report relates only to the items tested.

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.

BTTG® and Shirley® are trade names of Shirley Technologies Ltd.

The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.

Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2023 Shirley Technologies Limited. All rights reserved.



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: onestopshop@bttg.co.uk
Website: www.bttg.co.uk

Date: 30 August 2023

Our Ref: 23/61308D1/08/23

Your Ref: ---

Page: 2 of 4

Client: The Sign AG

Testing BS 5852: Clause 11: 2006 (2011) Assessment of the ignitability of upholstered seating by Smouldering and Flaming sources – Source 5 (Crib 5)

Pre-Treatment

The material received no pre-treatment as the fabric is stated not to be FR treated.

Conditioning

The sample was conditioned in the environments specified in Clause 10 of BS 5852: 2006 (2011).

Testing

The material was tested according to BS 5852:2006 (2011) Methods of test for the ignitability of upholstered composites for seating by flaming sources using Source 5 (Crib 5).

The sample was tested at 21°C and 59% relative humidity (R.H.).

The sample was tested over combustion modified polyurethane foam with a density of approximately 34-36kg/m³.



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
BTTG® and Shirley® are trade names of Shirley Technologies Ltd.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2023 Shirley Technologies Limited. All rights reserved.



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
 Telephone: +44 (0) 113 259 1999
 Email: onestopshop@bttg.co.uk
 Website: www.bttg.co.uk

Date: 30 August 2023
 Our Ref: 23/61308D1/08/23
 Your Ref: ---
 Page: 3 of 4

Client: The Sign AG

Results

The following test results relate only to the ignitability of the combination of upholstery composites under the particular conditions of test stated; they are not intended as a means of assessing the full potential fire hazard of the materials or products in use.

	Specimen 1
Time of Ignition (mins/secs)	0.13
Time of Flame Extinction (mins/secs)	>10.05 ME
Time of Smoke Extinction (mins/secs)	>10.05 ME
Time of cover split (mins/secs)	DNO
Extent of damage (mm) - Seat	
Width	209
Length	127
Depth	48
Extent of damage (mm) - Back	
Width	231
Depth	39
Melting	No
Dripping	No
Charring	Yes
Comments and Observations	ME/DNO
Specimen Result (Ignition or Non-ignition)	Ignition

Acronyms

ME – Manually extinguished
 DNO – Did not observe time of events

EC – Escalating combustion
 BTT – Burnt through thickness of foam

DNS – Material did not split
 BTE – Burnt to extremities





Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: onestopshop@bttg.co.uk
Website: www.bttg.co.uk

Date: 30 August 2023

Our Ref: 23/61308D1/08/23

Your Ref: ---

Page: 4 of 4

Client: **The Sign AG**

Comment

The results indicate 'Ignition' of the materials and the test is designated I/5 (ie. Fail).

Where required to make a judgement to any pass/fail criteria an estimation of uncertainty of measurement has been taken into account. Under our Policy we have used a non-binary decision rule.

See our decision rules Policy (<https://www.bttg.co.uk/about-us/decision-rules-policy/>) for further information.

Uncertainty Budget

Measurements: ± 2 mm

Timings: ± 2 seconds

Reported by:..... R Greasley, Laboratory Technician

Countersigned by:..... B Bland, Technical Customer Service Officer

Enquiries concerning this report should be addressed to Customer Services.



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
BTTG® and Shirley® are trade names of Shirley Technologies Ltd.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2023 Shirley Technologies Limited. All rights reserved.