



AMERICAN FLAMECOAT INC.

520 Eagleton Downs Drive - D
Pineville, NC 28134
O: 704.405.2550
F: 704.543.9772
www.americanflamecoat.com

February 6, 2024

thesign / AG
NEUSEELAND 32
9404 RORSCHACHERBERG
SWITZERLAND

Reference: Flammability Test Report: 114935

One (1) fabric sample identified as thesign/AG – MORI 30784, was received and tested in accordance with the California Technical Bulletin 117-2013, Section 1, Cover Fabric Test. The results are as follows:

<u>Test Results</u>		
Vertical Char Lengths		
16mm	17mm	16mm

The sample **meets** the requirements of the above standard. There were no ignitions or smoldering after 45 minutes on any of the three (3) specimens tested. In addition, none of the of the three test specimens displayed a char which was equal to or greater than 45mm.

If there are any questions or if we can be of further assistance, please let us know.

Sincerely,

Brad Souffrant
President

