

Confidential Report

Our Ref: 23/61562G1/11/23







Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

Date: 24 November 2023

Our Ref: 23/61562G1/11/23

Your Ref: ---

Page: 1 of 4

Client: Thesign AG

thesign SIAG Heimtextillen AG Neuseeland 32 CH-9404 Rorschacherberg Switzerland

Job Title: Fire Test on One Fabric Sample

Clients Order Ref: ---

Date of Receipt: 14 November 2023

Date Test Started: 23 November 2023

Description of Sample: One sample of fabric, which was referenced by the client as;

Victoria - 30661

Work Requested: We were asked to make the following fire test:

BS 5852: Clause 11:2006 (2011)

- * subcontracted test, UKAS accredited
- ** subcontracted test, EN ISO/IEC 17025 accredited
- *** not UKAS accredited



Note: This report relates only to the items tested.



Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

Date: 24 November 2023

Our Ref: 23/61562G1/11/23

Your Ref: ---

Page: 2 of 4

Client: Thesign AG

Testing BS 5852: Clause 11: 2006 (2011) Assessment of the ignitability of upholstered seating by Smouldering and Flaming sources – Source 5 (Crib 5)

Pre-Treatment

The material received no pre-treatment as the fabric is stated not to be FR treated.

Conditioning

The sample was conditioned in the environments specified in Clause 10 of BS 5852: 2006 (2011).

Testing

The material was tested according to BS 5852:2006 (2011) Methods of test for the ignitability of upholstered composites for seating by flaming sources using Source 5 (Crib 5).

The sample was tested at 19°C and 61% relative humidity (R.H.).

The sample was tested over combustion modified polyurethane foam with a density of approximately 34-36kg/m³.







Page:

Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

24 November 2023 Date:

Our Ref: 23/61562G1/11/23 Your Ref:

3 of 4

Client: Thesign AG

Results

The following test results relate only to the ignitability of the combination of upholstery composites under the particular conditions of test stated; they are not intended as a means of assessing the full potential fire hazard of the materials or products in use.

	Specimen 1
Time of Ignition (mins/secs)	0.13
Time of Flame Extinction (mins/secs)	>3.09 EC/ME
Time of Smoke Extinction (mins/secs)	>3.09 EC/ME
Time of cover split (mins/secs)	0.47
Extent of damage (mm) - Seat	
Width	226
Length	164
Depth	63
Extent of damage (mm) - Back	
Width	217
Depth	>75 BTT
Melting	No
Dripping	No
Charring	Yes
Comments and Observations	EC/ME/BTT
Specimen Result (Ignition or Non-ignition)	Ignition

Acronyms

ME – Manually extinguished DNO – Did not observe time of events EC – Escalating combustion BTT – Burnt through thickness of foam DNS - Material did not split BTE - Burnt to extremities







Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

24 November 2023 Date:

Our Ref: 23/61562G1/11/23

Your Ref:

Page: 4 of 4

Client: Thesign AG

Comment

The results indicate 'Ignition' of the materials and the test is designated I/5 (ie. Fail).

Where required to make a judgement to any pass/fail criteria an estimation of uncertainty of measurement has been taken into account. Under our Policy we have used a non-binary decision rule.

See our decision rules Policy (https://www.bttg.co.uk/about-us/decision-rules-policy/) for further information.

Uncertainty Budget

Measurements: ± 2 mm Timings: ± 2 seconds

Reported by:..... R Greasley, Laboratory Technician

...... B Bland, Technical Customer Service Officer Countersigned by:.....

Enquiries concerning this report should be addressed to Customer Services.



