



AMERICAN FLAMECOAT INC.

520 Eagleton Downs Drive - D  
Pineville, NC 28134  
O: 704.405.2550  
F: 704.543.9772  
[www.americanflamecoat.com](http://www.americanflamecoat.com)

July 23, 2024

thesign / AG  
NEUSEELAND 32  
9404 RORSCHACHERBERG  
SWITZERLAND

Reference: Flammability Test Report: 117997

One (1) fabric sample identified as thesign/AG – **30832 treated with FLAMECOAT**, was received and tested in accordance with the California Technical Bulletin 117-2013, Section 1, Cover Fabric Test. The results are as follows:

Test Results  
Vertical Char Lengths

27mm

25mm

28mm

The sample **meets** the requirements of the above standard. There were no ignitions or smoldering after 45 minutes on any of the three (3) specimens tested. In addition, none of the of the three test specimens displayed a char which was equal to or greater than 45mm.

If there are any questions or if we can be of further assistance, please let us know.

Sincerely,

Brad Souffrant  
President

