

American Flamecoat inc.

520 Eagleton Downs Drive - D Pineville, NC 28134 O: 704.405.2550 F: 704.543.9772 www.americanflamecoat.com

thesign / AG NEUSEELAND 32 9404 RORSCHACHERBERG SWITZERLAND

Pattern: **30831– treated with FLAMECOAT** Report No.: 117906 Date: July 16, 2024

TEST RESULTS

NATIONAL FIRE PROTECTION ASSOCIATION STD.701-2019 – TEST 1 Small Scale

Specimen	Residues (seconds)	Weight loss (%)
1	0.0	30.44
2	0.0	37.86
3	0.0	41.57
4	0.0	43.68
5	0.0	34.05
6	0.0	33.86
7	0.0	35.18
8	0.0	39.13
9	0.0	38.45
10	0.0	30.16
Average	0.0	36.44

Results: The Above Tested Material *meets* the Requirement

Requirements:

Average percent weight loss can-not exceed 40% and any individual specimen can-not exceed mean value plus three standard deviations.

Residue Flame:

Shall not continue to flame after reaching the floor of the tester for more than an average of two seconds per specimen for the sample of 10 specimens.

Sincerely,

Brad Souffrant President



Global FR, Fibercare Stain, Increase double rubs, Testing & On-Site